

How long after I hone and polish a marble floor can I recrystallize it?

As mentioned above, the recrystallization process does not like moisture. The floor needs to be dry before recrystallization is applied. It may take at least 24 hours for the floor to dry depending on humidity and temperature. Purchase a moisture meter and check the floor. Recrystallize only after the floor is dry.

TIP If you intend to use the recrystallization process after honing, it is best to wait at least 24 hours before applying the recrystallization process.

Online URL:

<https://surfacecarepros.com/kb/article/how-long-after-i-hone-and-polish-a-marble-floor-can-i-re-crystallize-it-1241.html>